Research Article

Magnetic Properties of FePt Nanoparticles Prepared by Sonoelectrodeposition

Nguyen Hoang Nam, Nguyen Thi Thanh Van, Nguyen Dang Phu, Tran Thi Hong, Nguyen Hoang Hai, and Nguyen Hoang Luong

VNU University of Science, 334 Nguyen Trai Road, Hanoi, Vietnam

Correspondence should be addressed to Nguyen Hoang Luong, luongnh@vnu.edu.vn

Received 24 March 2012; Accepted 26 April 2012

Academic Editor: Leonard Deepak Francis

Copyright © 2012 Nguyen Hoang Nam et al. This is an open access article distributed under the Creative Commons Attribution License, which permits unrestricted use, distribution, and reproduction in any medium, provided the original work is properly cited.

Sonoelectrodeposition is a useful technique to make metallic nanoparticles, using ultrasound during electrodeposition to remove nanoparticles as they grow on the cathode surface. This paper reports some structural and magnetic properties of FePt nanoparticles prepared by this method. The as-prepared $Fe_{45}Pt_{55}$ nanoparticles were ferromagnetic at room temperature. Upon annealing at 700°C for 1 h under H₂ atmosphere, the saturation magnetization and the coercivity of the nanoparticles were improved significantly. The annealed nanoparticles showed a high coercivity of 13.5 kOe at 2 K and of 9 kOe at room temperature. Sonoelectrodeposition is a promising technique to make large quantity of FePt nanoparticles.

1. Introduction

The ordered face-centered tetragonal (fct) L1₀ FePt materials are normally obtained from the disordered face-centered cubic (fcc) materials via the order-disorder transition. The ordered FePt alloys possess excellent hard magnetic properties with the saturation magnetization, $\mu_0 M_s$, of 1.4 T, the Currie temperature, T_c , of 750 K, and the crystalline anisotropy K_1 , of 7 MJ/m³ [1]. Despite the high cost of Pt, FePt thin films or particles have been paid much attention to their use as ultrahigh density magnetic storage media and microelectronic mechanical system (MEMS) due to the mechanical and chemical stability of the ordered fct L1₀ structure.

There are several ways to make FePt-nanostructured materials including physical techniques such as mechanical deformation [2], arcmelting [3], vacuum evaporation (sputtering and thermal evaporation) [4, 5], laser ablation pulse [6], chemical methods [7–9], and physicochemical method such as electrodeposition [10, 11]. Up to now, the vacuum evaporation is the most used method. Electrodeposition is a promising way to obtain FePt thin films because it is less expensive than physical methods, less complicated than chemical methods. But by this technique, it is difficult to

get nanoparticles with large quantity. Sonoelectrochemistry was developed to make nanoparticles [12]. It combined the advantages of sonochemistry and electrodeposition. Sonochemistry is a very useful synthetic method which was discovered as early as 1934 that the application of ultrasonic energy could increase the rate of electrolytic water cleavage. The effects of ultrasonic radiation on chemical reactions are due to the very high temperatures and pressures, which develop in and around the collapsing bubble [13]. Sonoelectrochemistry has the potential benefit of combining sonochemistry with electrochemistry. Some of these beneficial effects include acceleration of mass transport, cleaning and degassing of the electrode surface, and an increased reaction rate [14]. In this paper, we report the use of the sonoelectrochemical method for the preparation of FePt nanoparticles. Recently, CoPt nanoparticles encapsulated in carbon cages prepared by sonoelectrodeposition have been reported by Luong et al. [15].

2. Experimental

The sonoelectrochemical device employed is similar to that described in [16]. A titanium horn with diameter of 1.3 cm acted as both the cathode and ultrasound emitter (Sonics



FIGURE 1: TEM images of the as-prepared (a) and annealed (b) Fe₄₅Pt₅₅ nanoparticles (700°C/1 h).

VCX 750). The electroactive part of the sonoelectrode was the planar circular surface at the bottom of the Ti horn. An isolating plastic jacket covered the immersed cylindrical part. This sonoelectrode produced a sonic pulse that immediately followed a current pulse. One pulse driver was used to control a galvanostat and the ultrasonic processor, which was adapted to work in the pulse mode. A home-made galvanostat (without using a reference electrode) was used to control the constant current regime. A platinum plate with a square of 1 cm^2 was used as a counter electrode. The current pulse was 15 mA/cm². The ultrasound power density was 100 W/cm^2 . The duration t_{on} of the current pulse was 0.5-0.8 s, then the current was turned off for a fixed duration t_{off} of 0.5 s. During t_{on} , FePt nanoparticles were deposited on the surface of the electrode. When the current was switched off, an ultrasound was activated to remove the nanoparticles from the electrode. The time of ultrasound was 0.3 s. The temperature during the reaction was room temperature. The volume of the electrolysis cell was 80 mL containing 1 mM H2PtCl6, 0.1 M FeSO4, and 0.525 M Na₂SO₄. The chemicals were mixed under N₂ atmosphere. The pH = 3 of the solution was controlled by H₂SO₄. After deposition, FePt nanoparticles were collected by using a centrifuge (Hettich Universal 320, 9000 rpm, 20 min). Nanoparticles were dried in air at 80°C for 20 min. All samples were annealed at 700°C for 1 h under H₂ atmosphere. The structure of the nanoparticles was analyzed by using a Bruker D5005 X-ray diffractometer (XRD). The particle morphology was obtained from a transmission electron microscope (TEM JEM1010-JEOL). The chemical composition of the FePt nanoparticles was studied by using an energy dispersion spectroscopy (EDS OXFORD-ISIS 300) and revealed that the chemical composition of our sample is Fe45Pt55. Magnetic measurements were conducted by using Quantum Design's superconducting quantum interference device (SQUID) with a magnetic field up to 50 kOe at temperature range from 2 K to 300 K.



FIGURE 2: XRD patterns (Cu K α radiation) of the as-prepared (bottom) and annealed (top) Fe₄₅Pt₅₅ nanoparticles compared to those of the intensities for L1₀ FePt (PDF file 431359) and for Pt (marked by the asterisks, PDF file 04–0802). The fundamental peaks of FePt structure were denoted by "*f*," and the superlattice peaks were denoted by "*s*."

3. Results and Discussion

Figure 1 is the TEM images of typical as-prepared and annealed samples. Particle size of the as-prepared $Fe_{45}Pt_{55}$ sample was 5–10 nm. After annealing the particle size increased to 10–25 nm due to the aggregation and particle growth. In addition, the size distribution of the annealed particles was larger than that of the as-prepared samples.

Figure 2 shows the XRD patterns of the as-prepared and the annealed $Fe_{45}Pt_{55}$ nanoparticles (700°C for 1 h). Before annealing, the XRD results showed the reflections of pure Pt structure, which is similar to other FePt thin films produced by electrodeposition [17]. However, authors in [17] thought that the reflections were from the disordered fcc phase. For the fcc phase, XRD results present only the fundamental reflections which are (111), (200), and (220). The fundamental reflections of the fcc FePt are close to the (111), (200), and (220) reflections of the Pt that make some scientists thought that they are of the fcc structure. We propose that XRD results from our as-prepared nanoparticles and from [17] are the peaks of only Pt. The reflections from Fe are very weak due to the fact that their atomic weight is much less than that of Pt which is similar to the XRD result of FePt foils prepared by cold deformation [18]. The Pt peaks in the as-prepared samples are broad due to the small size of the particles. Using the Scherrer formula with the full width at half maximum of the strongest peak (111), the mean particle size of Pt particles was deduced to be 5.2 nm, which is much smaller than the particle size obtained from the TEM image. The particles were not disordered FePt, but they can be formed by many small domains of pure Fe and Pt. The formation of FePt by electrodeposition did not occurr and may be ascribed to the large difference in the standard electrode potential of the Fe^{2+}/Fe (-0.44 V [19]) and Pt⁴⁺/Pt (0.742 V [20]). Upon annealing, the formation of the ordered L1₀ fct phase happened by the diffusion process between Fe and Pt domains.

Magnetic measurements revealed low-saturation magnetization (M_s) and coercivity (H_c) in all as-prepared samples (data not shown). The saturation magnetization of the unannealed particles was about few emu/g and the coercivity was 20-80 kOe. The low value of M_s of the asprepared nanoparticles may be explained by the oxidation or hydroxidation of Fe atoms in nanoparticles, which can result in the weak magnetic iron oxides and iron hydroxides. This is in agreement with the suggestion of separated Fe and Pt domains in as-prepared nanoparticles. It is known that FePt with high-saturation magnetization is a chemically stable material. Therefore, it is difficult to be oxidized to form weak ferromagnetic materials. After annealing, the hard magnetic FePt phase was formed. Figure 3 presents the magnetic curves of the annealed Fe45Pt55 at different temperatures. The curves show a typical hard magnetic hysteresis loops with high H_c . Beside, form of the magnetic curves shows that a small soft magnetic phase, probably FePt₃, exists in the sample. The as-prepared Fe45Pt55 nanoparticles were ferromagnetic at room temperature. Upon annealing at 700°C for 1 h, the saturation magnetization and the coercivity of the nanoparticles were improved significantly. Coercivity of annealed Fe45Pt55 nanoparticles as a function of temperature is shown in Figure 4. At 2 K, the coercivity is 13.5 kOe and slightly decreases with increasing temperature to the value of 9 kOe at 300 K.

Magnetic squareness $S = M_r/M_s$ of annealed Fe₄₅Pt₅₅ nanoparticles as a function of temperature is shown in Figure 5. The temperature dependence of *S* is similar to that of H_c . At 2 K, the magnetic squareness is 0.78, slightly decreases with increasing temperature, and has a value of 0.745 at 300 K. This value of *S* is very close to that obtained for L1₀CoPt nanoparticles at room temperature [15].



FIGURE 3: Magnetic curves of annealed $Fe_{45}Pt_{55}$ nanoparticles at different temperatures.



FIGURE 4: Coercivity of annealed $Fe_{45}Pt_{55}$ nanoparticles as a function of temperature.

4. Conclusion

Sonoelectrochemistry is a promising method to make FePt magnetic nanoparticles. The annealed FePt nanoparticles made by this technique had the size of 10–25 nm. After annealing, the nanoparticles showed a high coercivity of 13.5 kOe at 2 K and 9 kOe at room temperature. This method possesses some advantages compared to common methods



FIGURE 5: Magnetic squareness $S = M_r/M_s$ of annealed Fe₄₅Pt₅₅ nanoparticles as a function of temperature.

such as simple preparation, low-cost equipment, and easy scaleup.

Acknowledgments

The authors would like to thank the National Foundation for Science and Technology Development of Vietnam-NAFOSTED (project 103.02.72.09) for financial support. N. H. Nam is grateful to the TRIG A Project of Hanoi University of Science, Vietnam National University, Hanoi for support to complete the paper at Nottingham University, Nottingham, United Kingdom. The authors would like to thank Professor Y. Nozue of Osaka University, Japan, for providing SQUID.

References

- A. Cebollada, R. F. C. Farrow, and M. F. Toney, "Structure and magnetic properties of chemically ordered magnetic binary alloys in thin film form," in *Magnetic Nanostructure*, H. S. Nalwa, Ed., p. 93, American Scientific, Stevenson Ranch, Calif, USA, 2002.
- [2] N. H. Hai, N. M. Dempsey, M. Veron, M. Verdier, and D. Givord, "An original route for the preparation of hard FePt," *Journal of Magnetism and Magnetic Materials*, vol. 257, no. 2-3, pp. L139–L145, 2003.
- [3] Q. I. Xiao, P. D. Thang, E. Brück, F. R. De Boer, and K. H. J. Buschow, "Effect of phase transformation on remanence enhancement in bulk Fe-Pt magnets," *Applied Physics Letters*, vol. 78, no. 23, pp. 3672–3674, 2001.
- [4] N. T. T. Van, N. H. Hai, N. H. Luong, V. V. Hiep, and N. Chau, "Magnetic properties of (FePt)_{100-x}Cu_x thin films," *Journal of the Korean Physical Society*, vol. 52, no. 5, pp. 1435–1438, 2008.
- [5] N. H. Luong, V. V. Hiep, D. M. Hong et al., "High-coercivity FePt sputtered films," *Journal of Magnetism and Magnetic Materials*, vol. 290-291, pp. 559–561, 2005.

- [6] L. J. Qiu, J. Ding, A. O. Adeyeye et al., "FePt patterned media fabricated by deep UV lithography followed by sputtering or PLD," *IEEE Transactions on Magnetics*, vol. 43, no. 6, pp. 2157– 2159, 2007.
- [7] S. Saita and S. Maenosono, "FePt nanoparticles with a narrow composition distribution synthesized via pyrolysis of iron(III) ethoxide and platinum(II) acetylacetonate," *Chemistry of Materials*, vol. 17, no. 14, pp. 3705–3710, 2005.
- [8] R. Harpeness and A. Gedanken, "The microwave-assisted polyol synthesis of nanosized hard magnetic material, FePt," *Journal of Materials Chemistry*, vol. 15, pp. 698–702, 2005.
- [9] S. Sun, C. B. Murray, D. Weller, L. Folks, and A. Moser, "Monodisperse FePt nanoparticles and ferromagnetic FePt nanocrystal superlattices," *Science*, vol. 287, no. 5460, pp. 1989–1992, 2000.
- [10] K. Žužek Rožman, A. Krause, K. Leistner, S. Fähler, L. Schultz, and H. Schlörb, "Electrodeposition and hard magnetic properties of Co-Pt films in comparison to Fe-Pt films," *Journal of Magnetism and Magnetic Materials*, vol. 314, no. 2, pp. 116– 121, 2007.
- [11] F. M. F. Rhen, G. Hinds, C. O'Reilly, and J. M. D. Coey, "Electrodeposited FePt films," *IEEE Transactions on Magnetics*, vol. 39, no. 5, pp. 2699–2701, 2003.
- [12] A. Gedanken, "Novel methods (sonochemistry, microwave heating, and sonoelectrochemistry) for the preparation of nanosized iorganic compounds," in *Inorganic Materials: Recent Advances*, D. Bahadur, S. Vitta, and O. Prakash, Eds., p. 302, Narosa Pu blishing, Delhi, India, 2002.
- [13] K. S. Suslick, S. B. Choe, A. A. Cichowlas, and M. W. Grinstaff, "Sonochemical synthesis of amorphous iron," *Nature*, vol. 353, no. 6343, pp. 414–416, 1991.
- [14] T. J. Mason, J. P. Lorimer, and D. J. Walton, "Sonoelectrochemistry," *Ultrasonics*, vol. 28, no. 5, pp. 333–337, 1990.
- [15] N. H. Luong, N. H. Hai, N. D. Phu, and D. A. MacLaren, "Co-Pt nanoparticles encapsulated in carbon cages prepared by sonoelectrodeposition," *Nanotechnology*, vol. 22, no. 28, Article ID 285603, 2011.
- [16] J. Zhu, S. T. Aruna, Y. Koltypin, and A. Gedanken, "A novel method for the preparation of lead selenide: pulse sonoelectrochemical synthesis of lead selenide nanoparticles," *Chemistry of Materials*, vol. 12, no. 1, pp. 143–147, 2000.
- [17] Q. Zeng, Y. Zhang, H. L. Wang, V. Papaefthymiou, and G. C. Hadjipanayis, "Magnetic properties and microstructure of fine Fe-Pt nanoparticles prepared by chemical reduction," *Journal* of Magnetism and Magnetic Materials, vol. 272–276, no. 1, pp. e1223–e1225, 2004.
- [18] N. H. Hai, N. M. Dempsey, and D. Givord, "Hard magnetic Fe-Pt alloys prepared by cold-deformation," *Journal of Magnetism and Magnetic Materials*, vol. 262, no. 3, pp. 353–360, 2003.
- [19] P. Atkins, *Physical Chemistry*, W.H. Freeman and Company, New York, NY, USA, 6th edition, 1997.
- [20] A. J. Bard and L. R. Faulkner, *Electrochemical Methods: Fundamentals and Applications*, John Wiley and Sons, New York, NY, USA, 2nd edition, 2001.